



Konstruktion Construction Description		1/10" Getuftete Schlinge, strukturiert 1/10" Tufted loop pile, structured 1/10" Bouclé tufté, structuré
Polnutschicht Pile material Composition de la fibre		100% PA 6
Strapazierwert Durability rating Usage	EN 1307	intensiv 32 32 intensive 32 intensif
Komfortwert Comfort class Confort		Komfortklasse LC2 Luxury class LC2 Classe confort LC2
Stuhlrolleneignung Castor chair use Effet d'une chaise à roulette		intensive Nutzung intensive use utilisation intensive
Gesamtdicke Total thickness Epaisseur totale	EN 1307	≈ 5,8 mm
Gesamtgewicht Total weight Poids total	EN 1307	≈ 1.700 g/m ²
Poleinsatzgewicht Pile weight Poids de velours	EN 1307	≈ 720 g/m ²
Brandverhalten Fire rating Comportement au feu	DIN EN 13501-1	C _{fl} -s1 ASTM E 648 + ASTM D2859
Trittschallschutz Impact noise insulation Isolation acoustique	DIN EN ISO 10140	26 dB
Schallabsorptionsgrad Sound absorption Absorption phonique	DIN EN ISO 354	α _w 0,15

Broadloom



